



CONTOPP®

RS 15 HD

Article n°: 20.256

KNOPP

Adolf-Oesterheld-Str. 1
D-97337 Dettelbach
Tel: +49(0)9324/9199-0
Fax: +49(0)9324/9199-66
info@knopp-chemie.com
www.knopp-chemie.com

Technical
datasheet

Function

- Quick to dry semi-dry sand/cement screeds within 9 days
- Increase in strength through synthetic hardening
- Load-dependent reduction of the screed thickness down to 30 mm
- Contains tracer for a subsequent half-quantitative analysis in sand/cement screeds
- Rehydration protection

Application area

- For producing bonded screeds and floating screeds
- For producing of non-standard thin-layered screeds
- For producing screeds on underfloor heating
- For damp or outside areas

Data

Colour:	Pink
Colour tracer-pigment:	red
Form:	liquid
Density (at 20 °C):	1.16 ± 0.01 g/ml
Processing temperature:	above + 5 °C
Shelf life	ca. 12 months – protect from frost and direct sunlight
Supply form:	PE-HD-can: 20 kg netto
	Container: 1,100 kg netto

Mix

	1 : 5 mix by weight	Standard	CONTOPP®	Unit
Cement		63	63	kg
Sand 0/8 ¹⁾		310	310	kg
RS 15 HD	-		1.3 ²⁾	ltr.
w/c-ratio		0.70 - 0.80	0.50 – 0.52	

Strength

Criteria	Standard	CONTOPP®	Unit
Flexural strength (28 days)	F5	F7	N/mm ²
Comp. strength (28 days)	C25	C40	N/mm ²
BRE test (impact resistance)	Category B	Category A	

Floor Finish

¹⁾according to EN 13139

²⁾corresponds to 2.0 V-% of the cement weight

This ideal screed mortar can only be manufactured whilst adhering to the processing information listed below. The details refer to 40 – 50mm screed thickness without UFH and 65 – 70mm screed thickness with UFH, normal climatic conditions at + 20°C and a relative humidity of 65%. Using sand with maximum grainsize < 8mm strength can be lower.

Criteria	Standard	CONTOPP®	Unit
Foot traffic	72	24	hours
Receive final floor finish	≥ 28	9	days

Basic materials

- CEM I or CEM II following EN 197.
- Aggregates following EN 12139.

Recipe

- **Stir the CONTOPP® RS 15 HD before use and regularly during use in order to prevent segregation!**
- Stick to the dosage (2.0 V-% of cement weight); ingredients should be added to the moistened mix. W/c-ratio < 0.52
- Mix for at least 2 minutes after adding all the components

PROPERTIES

TECHNICAL DATA

PROCESSING INFORMATION



Construction site conditions

- Protect from draughts and direct sunlight during setting.
- Remove surplus moisture by means of draught-free ventilation (natural ventilation).
- Nature of construction and site preparation following general codes of practice.

Minimum screed thickness ¹⁾

Flexural strength	Bonded	Unbonded	Floating	on underfloor heating ^{2) 3)}
7 N/mm ²	Standard: 20 mm Heavy duty: 20 mm	Standard: 30 mm Heavy duty: 35 mm	Standard: 35 mm Heavy duty: 40 mm	Standard: 35 mm Heavy duty: 40 mm

¹⁾ Working load: Standard ≤ 2.0 kN/m²; Heavy duty: ≤ 3.5 kN/m²

²⁾ In the case of screeds on underfloor heating thickness above the pipes

³⁾ No steel reinforcement required

Drying time ^{1) 2)}

Screed thickness	20 mm	30 mm	40 mm	50 mm	60 mm	70 mm
≤ 3.0 CM-% residual humidity ²⁾	1 days	3 days	6 days	9 days	13 days	18 days

¹⁾ Normal climatic conditions at + 20 °C and a relative humidity of 65 %

²⁾ The residual moisture content must be tested prior to the application of the final floor finish (CM-method).

Screed on underfloor heating - start-up heating protocol ^{1) 2)}

Heating process ³⁾	3 th day	4 th day	5 th day	6 th day	7 th day	8 th day	9 th day	10 th day
Temperature	25°C	35°C	45°C	55°C	55°C	45°C	35°C	25°C

¹⁾ It can be useful to lengthen the heating procedure for screed thicknesses of > 50 mm above the pipes to achieve sufficient drying.

²⁾ During the heating phase do not carry out any finishing work and do not cover or block the screed surface.

³⁾ UFH must be switched off during the laying of the screed.

Measuring residual moisture content

- Prior to laying the top flooring, the residual moisture of the screed must be measured by the person laying the floor.
- According to the KNOPP's manufacturers advice all floor coverings must be laid under a residual moisture content of 3.0 % using the carbide bomb measuring device (corresponds to approx. 4.5 Tramex reading – to be used only as indicator test).

Health & Safety

- Always observe general work hygiene when using our products.
- CONTOPP® accelerator systems are solvent-free and chloride-free.
- Our products do not deteriorate when stored properly (see data). Therefore, the stability and reactivity are not affected by storage.
- Find out more information on handling CONTOPP® accelerators from our safety data sheets.

Standards and testing regulations

- EN 13139: Aggregates for mortar
- EN 197: Cement – Part 1: Composition, specifications and conformity criteria for common cements

Comments

The raw materials we process and the products we produce are subject to strict factory inspections. Do not use products from other manufacturers when using this product. It is stressed that our products and the procedure must be tested for suitability for the expected construction site conditions. The quality of screeds is essentially influenced by the quality of sand and cement, the mixing rates and the processing in accordance with approved screeding technology. Upon the publication all other previous copies shall become invalid.

Stand 01.08.2024

SPECIAL INFORMATION

GENERAL INFORMATION