

CONTOPP®

FROST-EX MO3

Adolf-Oesterheld-Str.1
D-97337 Dettelbach
Tel: +49(0)9324/9199-0
info@knopp-chemie.com
knopp-chemie.com

PROPERTIES

PRODUCT DESCRIPTION

- Frost-Ex MO3 leads to an acceleration of the hydration of the cement and therefore the hardening of the concrete.
- The necessary compression strength of the concrete (in excess of 5 N/mm²) for frost protection will be obtained within a short period of time.
- EMICODE EC1^{plus}

APPLICATION AREA

- For producing unreinforced mortar for winter applications under ambient temperature between 5 to -10°C.
- For producing bonded screeds and floating screeds in line with BS 8204-1.
- For producing screeds on underfloor heating.
- For damp or outdoor areas.



TECHNICAL DATA

CHARACTERISTICS

Colour:	whitish-cloudy
Form:	liquid
Processing temperature:	above + 5 °C
Shelf life:	Approx. 12 months – protect from frost and direct sunlight
Supply form:	Disposable container: PE-HD-can: 24 kg total Reusable container: Container: 1200 kg total

DOSAGE

Ambient temperature	Amount per 50 kg cement	Unit
0 to -5°C	300	ml
-5 to -8°C	550	ml
-8 to -10°C	700	ml

Required amount of admixture according to requirements, base material, and construction site conditions following BS 8204-1 and BS EN 13813.

PROCESSING INFORMATION

BASIC MATERIALS

- OPC or blends following EN 197-1
- Aggregates following EN 12620

RECIPE

- Frost-Ex MO3 should be added either simultaneously with the mixing water or last of all.
- Generally ensure sufficient mixing time.
- Do not use frozen aggregates and do not concrete frozen reinforcements and shuttering.
- Fresh concrete temperature when applying the shuttering – at least + 5° C
- Protect the freshly applied concrete from any rapid loss of moisture or heat, until a compression strength of at least 5 N/mm² has been reached (initiate winter construction measures).

CONSTRUCTION CLIMATE CONDITIONS

- Protect from draughts and direct sunlight during setting.
- Remove excess moisture through draft-free cross-ventilation (4 times a day for 20–30 minutes).
- Nature of construction and site preparation following general codes of practice.

GENERAL INFORMATION

COMPATIBILITY WITH PRODUCTS OF THE CONTOPP® RANGE

- Frost-Ex MO3 can generally be used in combination with other additives from the CONTOPP® range.
- It is recommended to carry out a first type test according to DIN EN 13813 beforehand.

SAFETY

- Subject to labelling „Xi“ irritant (R 36/37/38: Irritating to eyes, respiratory system and skin.)
- Not hazardous goods as defined by transport regulations.
- WHC 1 (self-assessment) little risk of pollution.
- You can find out more information on handling Frost-Ex MO3 from our safety data sheets.

STANDARDS AND TESTING REGULATIONS

- BS 8204: In-situ floorings – bases and screeds
- BS 8000: Code of practice for cement/sand floor screeds and concrete floor toppings
- BS EN 13813: Screed material and floor screeds
- BS EN 13139: Aggregates for mortar
- EN 197: Cement – Part 1: Composition, specifications and conformity criteria for common cements

COMMENTS

The raw materials we process and the products we produce are subject to strict factory inspections. Do not use products from other manufacturers when using this product. It is stressed that our products and the procedure must be tested for suitability for the expected construction site conditions. The quality of screeds is essentially influenced by the quality of sand and cement, the mixing rates and the processing in accordance with approved screeding technology. Since we have no control over site conditions or construction practices, no legal liability can be derived from this technical data sheet. Upon the publication all other previous copies shall become invalid.

Last updated: 24.09.2026